



SOLTEC



PORTOFINO & PORTOBELLO

Rigid core SPC with integrated acoustical underlay

Essential data

0,55

mm
wear
layer

1,50

mm
integrated
underlayer

6,00

mm
total
thickness



vertical
drop lock

21

dB
acoustical
insulation

9300 gr

weight pro sqm

Bfl-S1

reaction
to fire

23|33|42

classification

V4

bevels



structured

Colours and designs



Our commitments



*25% recycled materials,
100% recyclable
using 30% renewable energy in production*

Contact us



Benoît DERAEDT

Chief Executive Officer &
Sales Europe & global

0032 493 52 98 58

benoit@soltec.be

Gilles DECOUTER

Internal sales

0032 56 92 19 92

gilles@soltec.be



Nele VERKEST

Finance & Administration Manager

0032 56 92 19 91

nele@soltec.be

GENERAL CONTACT DETAILS

Kortrijkstraat 19/0001

B-8580 Avelgem

BELGIUM



”

Thanks to our expertise in sourcing, logistics, and modern stock management – and with a central warehouse of over 250,000 m² in Belgium – we're always ready to serve customers across Europe and worldwide with unmatched speed.

Technical data sheet

Specification	Norm	Value PORTOFINO	Value PORTOBELLO
Classification	EN ISO 10874	23 33 42	23 33 42
Dimensions	EN ISO 24342	17,80 x 121,80 cm (planks) 30,48 x 60,96 cm (tiles)	22,60 x 153,50 cm
Box content		8 planks 10 tiles	6 planks
Surface pro box		1,73 sqm (planks) 1,86 sqm (tiles)	2,08 sqm (planks)
Total thickness	EN ISO 24346	6,00 mm (4,5 mm SPC + 1,5 mm IXPE)	6,00 mm (4,5 mm SPC + 1,5 mm IXPE)
Thickness of wear layer	EN ISO 24340	0,55 mm	0,55 mm
Total weight	EN ISO 23997	9300 gr/sqm	9300 gr/sqm
Surface protection		Polyurethane (PU)	Polyurethane (PU)
Embossing		Structured	Structured
Bevelled edges		V4	V4
Installation method		I4F vertical drop lock	I4F vertical drop lock
Dimensional stability	EN ISO 23999	≤ 0,10 %	≤ 0,10 %
Residual indentation	EN ISO 24341-1	≤ 0,10 mm	≤ 0,10 mm
Acoustical impact noise reduction	EN ISO 717-2	21 dB	21 dB
Light stability	EN ISO 105-B02	6 - 7	6 - 7
Resistance to household chemicals		OK	OK
Slipresistance	EN 13893 DIN 51130	> 0,30 R10	> 0,30 R10
Underfloor heating suitable	EN ISO 12524	OK max 30 °C	OK max 30 °C
Reaction to fire	EN ISO 13501-1	Bfl-S1	Bfl-S1
Use of solar energy		30 %	30 %
Re-use of water		30 %	30 %