

# SOLTEC



## PORTOFINO & PORTOBELLO

Rigid core SPC with integrated acoustical underlay

# Essential data

**0,55**

mm  
wear  
layer

**1,50**

mm  
integrated  
underlayer

**6,00**

mm  
total  
thickness



vertical  
drop lock

**21**

dB  
acoustical  
insulation

**9300** gr

weight pro sqm

**Bfl-S1**

reaction  
to fire

**23|33|42**

classification

**V4**

bevels



structured

# Colours and designs



# Our commitments



*25% recycled materials,  
100% recyclable  
using 30% renewable energy in production*

# Contact us



**Benoît DERAEDT**

Chief Executive Officer &  
Sales Europe & global

0032 493 52 98 58

benoit@soltec.be

**Laura SLOS**

Internal sales

0032 56 92 19 90

laura@soltec.be



**Nele VERKEST**

Finance & Administration Manager

0032 56 92 19 91

nele@soltec.be

**GENERAL CONTACT DETAILS**

Kortrijkstraat 19/0001

B-8580 Avelgem

BELGIUM



*Thanks to our expertise in sourcing, logistics, and modern stock management – and with a central warehouse of over 250,000 m<sup>2</sup> in Belgium – we're always ready to serve customers across Europe and worldwide with unmatched speed.*

# Technical data sheet

Specification	Norm	Value PORTOFINO	Value PORTOBELLO
Classification	EN ISO 10874	23   33   42	23   33   42
Dimensions	EN ISO 24342	17,80 x 121,80 cm (planks) 30,48 x 60,96 cm (tiles)	22,60 x 153,50 cm
Box content		8 planks 10 tiles	6 planks
Surface pro box		1,73 sqm (planks) 1,86 sqm (tiles)	2,08 sqm (planks)
Total thickness	EN ISO 24346	6,00 mm (4,5 mm SPC + 1,5 mm IXPE)	6,00 mm (4,5 mm SPC + 1,5 mm IXPE)
Thickness of wear layer	EN ISO 24340	0,55 mm	0,55 mm
Total weight	EN ISO 23997	9300 gr/sqm	9300 gr/sqm
Surface protection		Polyurethane (PU)	Polyurethane (PU)
Embossing		Structured	Structured
Bevelled edges		V4	V4
Installation method		I4F vertical drop lock	I4F vertical drop lock
Dimensional stability	EN ISO 23999	≤ 0,10 %	≤ 0,10 %
Residual indentation	EN ISO 24341-1	≤ 0,10 mm	≤ 0,10 mm
Acoustical impact noise reduction	EN ISO 717-2	21 dB	21 dB
Light stability	EN ISO 105-B02	6 - 7	6 - 7
Resistance to household chemicals		OK	OK
Slipresistance	EN 13893 DIN 51130	> 0,30 R10	> 0,30 R10
Underfloor heating suitable	EN ISO 12524	OK max 30 °C	OK max 30 °C
Reaction to fire	EN ISO 13501-1	Bfl-S1	Bfl-S1
Use of solar energy		30 %	30 %
Re-use of water		30 %	30 %