



# SOLTEC



# BOSTON+

Multi layer LVT Loose lay product with antislip backing

# Essential data

**0,70**

mm  
wear  
layer

**5,00**

mm  
total  
thickness

**13**

dB  
acoustical  
insulation

**V4**

bevels

**9300** gr

weight pro sqm

**Bfl-S1**

reaction  
to fire

**23|34|43**

classification



structured



*Find out all about our collection on  
the product page!*

**SOLTEC**  
Premium

# Colours and designs

” *Boston+ brings natural character to even the toughest spaces—six striking décors backed by a 0.70 mm wear layer for true, lasting performance.*



# Our commitments



*25% recycled materials,  
100% recyclable  
using 30% renewable energy in production*

# Contact us



**Benoît DERAEDT**

Chief Executive Officer &  
Sales Europe & global

0032 493 52 98 58

benoit@soltec.be

**Laura SLOS**

Internal sales

0032 56 92 19 90

laura@soltec.be



**Nele VERKEST**

Finance & Administration Manager

0032 56 92 19 91

nele@soltec.be

**GENERAL CONTACT DETAILS**

Kortrijkstraat 19/0001

B-8580 Avelgem

BELGIUM



*Thanks to our expertise in sourcing, logistics, and modern stock management – and with a central warehouse of over 250,000 m<sup>2</sup> in Belgium – we're always ready to serve customers across Europe and worldwide with unmatched speed.*

# Technical data sheet

Specification	Norm	Value
Classification	EN ISO 10874	23   34   43
Dimensions	EN ISO 24342	22,86 x 121,92 cm (planks) 91,44 x 91,44 cm (tiles)
Box content		6 planks 4 tiles
Surface pro box		1,67 sqm (planks) 3,34 sqm (tiles)
Total thickness	EN ISO 24346	5,00 mm
Thickness of wear layer	EN ISO 24340	0,70 mm
Total weight	EN ISO 23997	9300 gr/sqm
Surface protection		Polyurethane (PU)
Embossing		Structured
Bevelled edges		V4
Installation method		Loose lay
Dimensional stability	EN ISO 23999	≤ 0,15 %
Residual indentation	EN ISO 24341-1	≤ 0,10 mm
Acoustical impact noise reduction	EN ISO 717-2	13 dB
Light stability	EN ISO 105-B02	≤ 6
Resistance to household chemicals		OK
Slipresistance	EN 13893 DIN 51130	> 0,30 R10
Underfloor heating suitable	EN ISO 12524	OK max 30 °C
Reaction to fire	EN ISO 13501-1	Bfl-S1
Use of solar energy		30 %
Re-use of water		30 %



Check out the full technical specifications!